



Zipro

Zipro Ceramic Material

DATA SHEET

Spray Dried Alumina

Chemical Analysis

Product Code	ZP-AL-S
Chemical Formula	Al ₂ O ₃
Composition	Analytical Value Typical Specifications
Al ₂ O ₃ (Min.%)	95
Fe ₂ O ₃ (Max.)	0.05
Na ₂ O(Max.)	0.25
Moisture(Max.)	0.5
Particle Size(Mesh)	40~300
Stacking Density (g/cm ³)	1.05~1.15
Average Shrinkage	16~18%
Sintering Density (g/cm ³)	3.65